GEOLOGICAL SURVEY OF WYOMING
MINERAL REPORT #MR 82-5

## ASSAY REPORT ON SELECTED DUMP SAMPLES FROM THE PORTLAND MINE, SIERRA MADRE, WYOMING

by W. Dan Hausel

The Portland Mine is located 4 mile south of the Battle village in the SW/4 sec. 29, T14N, R85W of the Sierra Madre (Figure 1). Two similar mines, the Portland and Hercules, are located about 100 yards of each other; the Portland lies to the west of the Hercules. The two mines lie on the contact of granite with chloritized mafic rock.

The mineralized rock is principally silicified mafic rock impregnated with chalcopyrite and lesser chalcocite. The granite is also partially mineralized. A sample of cupriferous chloritized mafic rock was selected for assay from the Portland mine dump and ran 2.75 percent copper, 0.008 percent zinc and no gold (Figure 2).




Figure 1. Location map of the Portland and Hercules mines (base map U.S. Geological Survey Red Mountain  $7\frac{1}{2}$ -minute quadrangle).



## WYOMING ANALYTICAL LABORATORIES, INC.

Box 638 @ 605 South Adams

(307) 742-7995

LARAMIE, WYOMING 82070

Dan Hausel Wyoming Geological Survey Box 3008, Univ. Sta. Laramie, WY 80434 Request No. 1349-063 Date: 13 October 1982

| REPORT OF ANALYSIS |        |  |       |                              |                                     |                                    |
|--------------------|--------|--|-------|------------------------------|-------------------------------------|------------------------------------|
| Customer ID        |        | (sec 29-14 N- 850<br>BP-1,Portland<br>Mine<br>9859 |       | ES-1, Oriole<br>Mine<br>9861 | ES6-8, Tender-<br>foot Mine<br>9862 | HP-18,<br>Fletcher<br>Park<br>9863 |
|                    |        |  |       | 2                            |                                     |                                    |
| Gold               | oz/ton | <0.01  | <0.01 |                              | <0.01                               | <0.01                              |
| Copper             | %      | 2.75   |       | 1.11                         |                                     | 0.135                              |
| Platinum           | oz/ton |  | <0.01 |                              | <u></u>                             |                                    |
| Silver             | oz/ton |  |       |                              |                                     | <0.01                              |
| Zinc               | mg/L   | 81.4   | \     |                              |                                     | 46.9                               |
|                    |        |  |       |                              |                                     |                                    |

Figure 2. Assay report on sample BP-1.